

# BIOCLEAN ULTIMATE

Sterile Polychloroprene Gloves  
**BUPS**

## About

BioClean Ultimate Sterile Polychloroprene Gloves offer good tactility for precision work and comfort for prolonged use. Offering resistance to a range of chemicals\* and antistatic properties the Ultimate is also latex-free and powder-free.

## Specifications

**COMPATIBILITY:**

ISO Class 4 & EU GMP Grade A

**LENGTH:**

300mm (12")

**MATERIAL:**

Polychloroprene

**PROTEIN LEVEL:**

Polychloroprene contains no natural latex proteins

**SURFACE:**

Textured

**SHAPE:**

Hand specific

**COLOUR:**

Natural

**STERILIZATION:**

Gamma irradiation


ANTISTATIC

CHEMICAL RESISTANCE\*

DOUBLE-DONNABLE

## Features

- Powder-free & latex-free
- ESD properties
- Beaded cuff for strength
- Chemical resistant\*
- Double-donnable
- Non-particulating EasyTear packaging



Ms.G.Love© represents BioClean's range of cleanroom gloves

## Quality Standards

- Manufactured in a facility holding ISO 9001: 2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 - Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Processed in an NEBB certified ISO Class 4 environment
- Complies with the requirements of Glove Standard EN420:2003 and EN374-1, 2 & 3:2003
- Physical properties comply with European Medical Glove Standard EN455-2:2009
- Tested against permeation standard ASTM D6978-05 for cytotoxic drugs
- Sterilized in accordance with ISO 11137-1:2006
- Suitable for contact with all foodstuffs.

## Physical Properties

CHARACTERISTICS	VALUE	TEST METHOD
Freedom From Holes	AQL 0.65 Performance Level 3	EN 374-2:2003
Glove Length +/-10mm (mm/inches)	290/11.4	EN 420:2003
Single Wall Thickness Minimum (mils/mm)	Cuff: 3.54/0.09 Palm: 4.33/0.11 Finger Tip: 5.51/0.14	EN 455-2:2009
Force At Break During Shelf Life	≥ 3.6 N	EN 455-2:2009

## Sterilization

Method: Gamma irradiation  
Minimum Dose: 25kGy  
Sterility Assurance Level: 10<sup>-6</sup>

## Shelf Life & Storage

Five (5) years from date of manufacture.  
Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

PALM WIDTHS (mm) ± 5mm							
SIZE	6.0	6.5	7.0	7.5	8.0	8.5	9.0
mm	77	83	89	95	102	108	115
TEST METHOD				EN 420:2003			

## Glove Cleanliness Characteristics

PARTICLES				TYPICAL PARTICLE COUNT				TEST METHOD
≥ 0.5µm(counts/cm <sup>2</sup> )				<1300				IEST-RP-CC005.4
TYPICAL EXTRACTABLE IONS								TEST METHOD
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.4
(µg/cm <sup>2</sup> )	ND	0.494	ND	ND	0.795	ND	0.041	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(µg/cm <sup>2</sup> )	ND	0.123	0.005	0.378	0.582	0.025	NT	
ND = Not Detected, NT = Not Tested, NA = Not Applicable								

## TO ORDER

Re-order code	Size	Packing
BUPS-60	6.0	One pair per inner PE wallet; one wallet per sealed EasyTear PE pouch; 10 pouches per sealed outer PE bag; 20 outer bags per lined carton (200 pairs)
BUPS-65	6.5	
BUPS-70	7.0	
BUPS-75	7.5	
BUPS-80	8.0	
BUPS-85	8.5	
BUPS-90	9.0	

For additional information visit us at [www.bioclean.com](http://www.bioclean.com), or call us at +44 1638 663338

**Nitritex Ltd**

Minton Enterprise Park  
Oaks Drive  
Newmarket, Suffolk  
CB8 7YY  
United Kingdom

BUPS/1806/PDS38



Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

\*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

\*\*Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2018 Ansell Limited. All Rights Reserved.