

CW-1000-PRF685/917

Hydroentangled blend of 55% cellulose / 45% polyester, lightweight.

Property	Typical Value	Test Method
Basis Weight		
(oz/yd ²)	1.6	
(g/m ²)	54	
Thickness		
(mils)	12	
(mm)	0.30	
Sorbency Capacity		
Intrinsic (mL/g)	6.5	IEST-RP-CC004.3
Extrinsic (mL/m ²)	336	IEST-RP-CC004.3
Nonvolatile Residue (NVR) (g/m²)		
Deionized Water	0.051	IEST-RP-CC004.3
Isopropyl Alcohol	0.030	IEST-RP-CC004.3
Ions (ppm)		
Sodium	96	IEST-RP-CC004.3
Chloride	66	IEST-RP-CC004.3
Particles (million/m²)		
0.5 - 5.0 µm	113	IEST-RP-CC004.3
5.0 µm and Larger	8.5	IEST-RP-CC004.3
Fibers (fibers/m²)		
>100 µm	203,110	IEST-RP-CC004.3

