

## PRODUCT SPECIFICATION

---

**HandPRO®**

**ROYAL TOUCH 300™**

**NITRILE EXAM GLOVES**

**240mm (9") Length**

Nitrile - Not Made with  
Natural Rubber Latex

Powder-Free

Non-Sterile

Chemotherapy Drug  
Permeation Tested

Finger-Textured Surface

Royal Blue Color

Double-Donnable

Ambidextrous

Beaded Cuff



ISO 374-1:2016/Type B ISO 374-5:2016



K P T



VIRUS



## QUALITY & CONFORMITY

- Manufactured under ISO 13485, ISO 9001, and US FDA QSR Quality Management System
- Conforms to ASTM D6319 and EN455
- EC Certificate 0321.10015-01.E00-00 (Type B, CE 0321)
- Complies with FDA CFR 21 177.2600 and European Commission Regulation (EU) No. 10/2011 for food handling
- Conforms to the following additional test standards:

ASTM D412	Tensile Properties of Vulcanized Rubbers
ASTM D3578	Standard Specification for Rubber Examination Gloves
ASTM D5151-99	Standard Test for Detection of Holes in Medical Gloves
ASTM D573	Accelerated Aging for Rubber (at 70° C for 166hr)
ASTM D6124	Test Method for Residual Powder on Medical Gloves
ASTM D6978	Tested for use with Chemotherapy Drugs
ASTM F1671-13	Viral Penetration Test

## PERFORMANCE REQUIREMENTS

Characteristic	Inspection Level	AQL
Freedom from Holes	G1	1.5
Visual Defects (Major)	G1	2.5
Visual Defects (Minor)	G1	4.0
Physical Properties	S2	4.0
Physical Dimensions	S2	4.0
Powder Residue	-	2mg/glove (Max)

## PHYSICAL DIMENSIONS

Size	X-Small (5/6)	Small (6/7)	Medium (7/8)	Large (8/9)	X-Large (9/10)
Palm Width $\pm$ 5 mm	75	85	95	106	116
Glove Length (mm)	Typical Value 245-246 (240 Minimum)				
Thickness (mm)	0.04 Minimum				
Cuff (25 $\pm$ 5 mm from bead)	Typical Value 0.06-0.07 (0.05 Minimum)				
Palm (center of palm)	Typical Value 0.11 (0.06 Minimum)				
Finger (13 $\pm$ 3 mm from tip)					

## PHYSICAL PROPERTIES

Test	Before Aging		After Aging	
	Minimum	Typical Value	Minimum	Typical Value
Tensile Strength (MPa)	14	25.59-29.04	14	27.60-31
Ultimate Elongation	500%	508-526%	400%	480-491%
Force at Break (Newton)	6.0	6.21-6.43	6.0	6.41-7.45

## ESD PROPERTIES

HandPRO® RoyalTouch300™ is a Static Dissipative Nitrile Exam Glove in use and meets ANSI/ESD S20.20-2014 requirements for compliance.



## PRODUCT NUMBERS

Size	Item #	Case Quantity
X-Small	300	3000
Small	301	3000
Medium	302	3000
Large	303	3000
X-Large*	304	2500

## PACKAGING

300 gloves per box, 10 boxes per case.  
\* Size XL 250 gloves per box, 10 boxes per case.

## SHELF LIFE & STORAGE

Three years from date of manufacture. Store in a cool, dry place away from direct sunlight.

The specifications provided reflect the minimum acceptable requirements of the ASTM and FDA where applicable. Actual testing results are available upon request. Gloves offered by Hourglass International, Inc. meet or exceed these physical requirements. Independent laboratory test results are available upon request.

Your Protection Is  
Our Purpose



 Hourglass-Intl.com  
 (800) 277-0994  
 hourglass-international-inc  
 hourglassinternationalinc  
 HourglassIntl

USA